

USINAGE PAR DEFORMATION PLASTIQUE	TCSM LP C. STOESSEL
Abaque des ΔL	Nom:

Ep	V	Ri	F	b	165°	150°	135°	120°	105°	90°	75°	60°	45°	30°	15°	0°
0.6	6	1	4	4	-0.1	-0.2	-0.4	-0.6	-0.8	-1.3	-1	-0.6	-0.3	0	+0.3	+0.7
	8	1.3	4	5.5	-0.1	-0.2	-0.4	-0.6	-0.9	-1.4	-1	-0.6	-0.2	+0.3	+0.7	+1
0.8	6	1	7	4	-0.1	-0.3	-0.5	-0.7	-1.1	-1.6	-1.3	-0.7	-0.6	-0.3	+0.1	+0.4
	8	1.3	5	5.5	-0.1	-0.3	-0.5	-0.7	-1.1	-1.7	-1.3	-0.8	-0.4	0	+0.4	+0.8
	10	1.6	4	7	-0.1	-0.3	-0.5	-0.8	-1.2	-1.8	-1.3	-0.8	-0.3	+0.2	+0.7	+1.2
1	6	1	11	4	-0.2	-0.4	-0.6	-0.9	-1.3	-1.9	-1.6	-1.2	-0.9	-0.5	-0.2	+0.2
	8	1.3	8	5.5	-0.2	-0.4	-0.6	-0.9	-1.4	-2	-1.6	-1.1	-0.7	-0.3	+0.2	+0.6
	10	1.6	7	7	-0.2	-0.4	-0.6	-0.9	-1.4	-2.1	-1.6	-1.1	-0.5	0	+0.5	+1
	12	2	6	8.5	-0.2	-0.4	-0.6	-1	-1.5	-2.2	-1.6	-1	-0.3	+0.3	+0.9	+1.6
1.2	6	1	16	4	-0.2	-0.5	-0.8	-1.1	-1.6	-2.3	-1.9	-1.5	-1.2	-0.8	-0.5	60.1
	8	1.3	12	3.5	-0.2	-0.5	-0.7	-1.1	-1.6	-2.3	-1.9	-1.4	-1	-0.6	-0.1	+0.3
	10	1.6	10	7	-0.2	-0.4	-0.7	-1.1	-1.6	-2.4	-1.9	-1.4	-0.8	-0.3	+0.2	+0.8
	12	2	8	8.5	-0.2	-0.4	-0.7	-1.1	-1.7	-2.5	-1.9	-1.3	-0.6	0	+0.7	+1.3
	16	2.6	6	11	-0.2	-0.4	-0.7	-1.2	-1.8	-2.7	-1.9	-1.1	-0.3	+0.5	-1.3	+2.1
1.5	8	1.3	17	5.5	-0.3	-0.6	-0.9	-1.4	-2	-2.8	-2.4	-1.9	-1.5	-1	-0.5	-0.1
	10	1.6	15	7	-0.3	-0.6	-0.9	-1.4	-2	-2.9	-2.4	-1.8	-1.3	-0.7	-0.2	+0.4
	12	2	13	8.5	-0.3	-0.6	-0.9	-1.4	-2.1	-3	-2.4	-1.7	-1	-0.4	+0.3	+1
	16	2.6	9	11	-0.3	-0.5	-0.9	-1.4	-2.1	-3.2	-2.4	-1.5	-0.7	+0.1	+1	+1.8
	20	3.3	8	14	-0.2	-0.5	-0.9	-1.4	-2.2	-3.4	-2.4	-1.4	-0.4	+0.7	+1.7	+2.7
2	10	1.6	27	7	-0.4	-0.8	-1.3	-1.9	-2.7	-3.7	-3.2	-2.6	-2	-1.4	-0.9	-0.3
	12	2	22	8.5	-0.4	-0.8	-1.2	-1.8	-2.7	-3.8	-3.1	-2.5	-1.8	-1.1	-0.4	+0.3
	16	2.6	17	11	-0.3	-0.7	-1.2	-1.9	-2.7	-4	-3.1	-2.3	-1.4	-0.5	+0.3	+1.2
	20	3.3	13	14	-0.3	-0.7	-1.2	-1.9	-2.8	-4.2	-3.2	-2.1	-1	0	+1.1	+2.2
	25	4	11	17.5	-0.3	-0.7	-1.2	-1.9	-2.9	-4.5	-3.2	-1.9	-0.7	+0.6	+1.8	+3.1
2.5	12	2	35	8.5	-0.5	-1	-1.6	-2.3	-3.3	-4.7	-4	-3.2	-2.5	-1.8	-1.1	+0.4
	16	2.6	26	11	-0.5	-0.9	-1.5	-2.3	-3.3	-4.8	-3.9	-3	-2.1	-1.2	-0.3	+0.6
	20	3.3	21	14	-0.4	-0.9	-1.5	-2.3	-3.4	-5	-3.9	-2.8	-1.7	-0.6	+0.5	+1.6
	25	4	17	17.5	-0.4	-0.9	-1.5	-2.3	-3.5	-5.2	-3.9	-2.6	-1.4	-0.1	+1.2	+2.5
	32	5	13	22	-0.4	-0.9	-1.5	-2.4	-3.6	-5.6	-4	-2.4	-0.8	+0.7	+2.3	+3.9
3	16	2.6	38	11	-0.6	-1.2	-1.9	-2.8	-4	-5.7	-4.7	-3.8	-2.9	-2	-1.1	-0.1
	20	3.3	30	14	-0.5	-1.1	-1.8	-2.8	-4	-5.8	-4.7	-3.6	-2.5	-1.3	-0.2	+0.9
	25	4	24	17.5	-0.5	-1.1	-1.8	-2.8	-4.1	-6	-4.7	-3.4	-2.1	-0.7	-0.6	+1.9
	32	5	19	22	-0.5	-1.1	-1.8	-2.8	-4.2	-6.3	-4.7	-3.1	-1.5	+0.1	+1.7	+3.3
	40	6.5	15	28	-0.5	-1	-1.8	-2.9	-4.5	-6.8	-4.8	-2.8	-0.8	+1.3	+3.3	+5.3
4	20	3.3	54	14	-0.7	-1.6	-2.5	-3.7	-5.3	-7.5	-6.3	-5.2	-4	-2.8	-1.6	-0.4
	25	4	42	17.5	-0.7	-1.5	-2.5	-3.7	-5.3	-7.7	-6.3	-4.9	-3.5	-2.1	-0.7	+0.7
	32	5	34	22	-0.7	-1.5	-2.4	-3.7	-5.4	-7.9	-6.3	-4.6	-2.9	-1.2	+0.4	+2.1
	40	6.5	27	28	-0.7	-1.4	-2.4	-3.7	-5.6	-8.4	-6.3	-4.2	-2.1	0	+2.1	+4.2
	50	8	21	35	-0.6	-1.2	-2.4	-3.8	-5.8	-8.9	-6.4	-3.9	-1.3	+1.2	+3.7	+6.2
5	25	4	67	17.5	-0.9	-1.9	-3.1	-4.6	-6.6	-9.4	-7.9	-6.5	-5.1	-3.6	-2.2	-0.7
	32	5	52	22	-0.9	-1.9	-3.1	-4.6	-6.7	-9.6	-7.9	-6.1	-4.4	-2.7	-0.9	+0.8
	40	6.5	42	28	-0.9	-1.8	-3	-4.6	-6.8	-10	-7.8	-5.7	-3.5	-1.3	+0.8	+3
	50	8	33	35	-0.8	-1.8	-3	-4.7	-7	-10	-7.9	-5.3	-2.7	-0.1	+2.5	+5.1
	63	10	26	45	-0.8	-1.7	-3	-4.7	-7.3	-11	-8	-4.8	-1.7	+1.5	+4.6	7.5
6	32	5	75	22	-1.1	-2.3	-3.8	-5.6	-8	-11	-9.5	-7.7	-5.9	-4.1	-2.3	-0.6
	40	6.5	60	28	-1.1	-2.3	-3.7	-5.5	-8.1	-12	-9.4	-7.2	-5	-2.7	-0.5	+1.7
	50	8	48	35	-1	-2.2	-3.6	-5.5	-8.2	-12	-9.4	-6.8	4.1	-1.4	+1.2	+3.9
	63	10	38	45	-1	-2.1	-3.6	-5.6	-8.5	-13	-9.5	-6.2	-3	+0.2	+3.4	+6.6
	80	13	30	55	-1	-2.1	-3.6	-5.7	-8.9	-14	-9.6	-5.6	-1.5	+2.5	+6.6	+11
8	63	10	68	45	-1.4	-2.9	-4.9	-7.4	-11	-16	-13	-9.2	-5.8	-2.5	-0.9	+4.2
	80	13	53	55	-1.3	-2.9	-4.8	-7.5	-11	-17	-13	-8.4	-4.2	0	+4.2	+8.4
	100	16	43	71	-1.3	-2.8	-4.8	-7.6	-12	-18	-13	-7.7	-2.7	+2.3	+7.4	+12